

## CONFIDENTIAL TEST REPORT

<b>To:</b>	<b>Report No:</b> T7818113 <b>Lab No:</b> T7818113 <b>Date Sampled:</b> 18/09/2013 <b>Date Received:</b> 18/09/2013 <b>Date Tested:</b> 18-23/09/2013 <b>Date Reported:</b> 18/09/13 <b>Customers Mark:</b> See Table <b>O/No:</b>
<b>FAO:</b>	

### BRADFORD FIRECLAY – SOIL HILL

SAMPLE ID	SAMPLE	SHRINKAGE % DRY - FIRED	SHRINKAGE % TOTAL	% Na <sub>2</sub> O	% MgO	% Al <sub>2</sub> O <sub>3</sub>	% SiO <sub>2</sub>	% P <sub>2</sub> O <sub>5</sub>	% K <sub>2</sub> O	% CaO	% TiO <sub>2</sub>	% Cr <sub>2</sub> O <sub>3</sub>	% MnO <sub>2</sub>	% Fe <sub>2</sub> O <sub>3</sub>	% LOI	% Carbon	% Sulphur
T7813113	FIRECLAY	1.4	3.8	0.21	2.21	21.20	70.07	0.67	1.16	0.29	1.57	0.03	0.03	2.56	9.23	0.51	0.078

Authorised Signatory:

#### ***D. Salt***

The results reported refer only to the sample tested. No responsibility is accepted for the representative nature of the sample unless it is obtained under our supervision. This report must not be reproduced in part without the written permission of Claysales Laboratories Ltd, nor used in any other way as to lead to the misrepresentation of the results.